

NitriDerm® Ultra Black

Nitrile Exam Gloves Series 187

This popular black color masks a variety of stains and is a true medical grade exam glove. Engineered with a medium modulus and high tensile strength, this glove is first choice for a wide range of end users including law enforcement and corrections. Textured for excellent grip. Tested to provide maximum protection from fentanyl exposure.

Characteristics: Sterile, Powder-Free, Black Color



SIZE	ITEM NO.
XS	187020
S	187100
M	187200
L	187300
XL	187350
XXL	187400
XXXL	187450

Features:

- Non-Latex = No Risk of Latex Allergens
- Textured Finish = Improved Wet/Dry Grip
- Low Modulus = a Softer, More Comfortable Fit

XS-XL : 100 Gloves/Box, 10 Boxes/Case
XXL-XXXL : 90 Gloves/Box, 10 Boxes/Case



Manufactured in compliance with multiple international standards, including ASTM D6319, ASTM D5151, ASTM F1671, and ASTM D6978

Tested for use with Chemotherapy Drugs as per ASTM D6978

Standard Practice for Assessment of Medical Gloves to Permeation by Chemotherapy Drugs

Minimum Breakthrough Detection Time in Minutes:

Carmustine (3.3 mg/ml)	23.3	Ifosfamide (50.0 mg/ml)	>240
Cisplatin (1.0 mg/ml)	>240	Methotrexate (25.0 mg/ml)	>240
Cyclophosphamide (20.0 mg/ml)	>240	Mitomycin C (0.5 mg/ml)	>240
Dacarbazine (10.0 mg/ml)	>240	Mitoxantrone (2.0 mg/ml)	>240
Doxorubicin Hydrochloride (2.0 mg/ml)	>240	Paclitaxel (6.0 mg/ml)	>240
Etoposide (20.0 mg/ml)	>240	Thiotepa (10.0 mg/ml)	58.2
Fluorouracil (50.0 mg/ml)	>240	Vincristine Sulfate (1.0 mg/ml)	>240
		Also Tested: Fentanyl Citrate (100 mcg/2ml)	>240

Please note that Carmustine and Thiotepa have extremely low permeation times of 23.3 minutes and 58.2 minutes respectively.

Caution: In compliance with ASTM D6978, the testing conditions used are intended to approximate the worst-case conditions for clinical use. Testing was conducted on single layer glove material. It is the users' responsibility to determine the applicability of these gloves for their intended use with chemotherapy drugs.

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	32	27
ASTM Requirement Min. (Mpa)	14	14
Elongation (%)	650	560
ASTM Requirement Min. (%)	500	400

Average Length	9.5 in ♦ 240 mm
Average Palm Thickness	4.0 mil ♦ 0.10 mm
Average Finger Thickness	5.5 mil ♦ 0.14 mm



Intertek

Innovative Healthcare Corporation is certified to ISO 13485:2016 QMS for medical devices.



**INNOVATIVE
HEALTHCARE
CORPORATION**

www.ihc-solutions.com

1-800-272-1533

Product Solutions You Trust

View this product on our website:

