

### Product Literature

#### **Characteristics**

The strong black color of Black Wolf™ makes a statement no matter where it's used. Black Wolf™ is manufactured with a very pure natural latex formulation, which allows for incredible strength and elasticity, as well as extraordinary comfort. It's the first choice of a wide range of professionals including; law enforcement, corrections, first responders, tattoo artists, professional piercers and many others. Textured surface provides an excellent grip. Dark Black color.



BLACK WOLF™ Latex Series 127 Exam Glove Non-Sterile



#### Features:

- Micro-Chlorinated for a Softer Feel
- Textured for an Improved Wet/Dry Grip
- Low Modulus for a Softer, More Comfortable Fit
- Low Protein for Reduced Changes of Latex Allergic Reactions

#### PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION	
XS	127050	100 Gloves/box, 10 boxes/case		
S	127100	100 Gloves/box, 10 boxes/case		
M	127200	100 Gloves/box, 10 boxes/case	Gloves, Exam, Latex, Non Sterile, Powder-Free, Textured, Black Color	
L	127300	100 Gloves/box, 10 boxes/case	1 owder-1 ree, rextured, black dolor	
XL	127350	100 Gloves/box, 10 boxes/case		

View this product on our website:



Product Solutions You Trust



## Specification Sheet

# BLACK WOLF







- 100 Qty (By Weight)
- Single Use
- Ambidextrous
- Non-Sterile

Black Wolf™ Latex is manufactured in compliance with multiple international standards, including the following:

Designation	Standard	
ASTM D3578 Standard Specification for Rubber Examination Gloves		
ASTM D5151 Standard Test Method for Detection of Holes in Medical Gloves		
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens	
ASTM D5712	Standard Test Method for Analysis of Aqueous Extractable Protein in Natural Rubber	

Average Length	Average Palm Thickness	Average Finger Thickness	
9.5 in <b>→</b> 240 mm	5.5 mil <b>◆</b> 0.14 mm	6.0 mil <b>◆</b> 0.15 mm	

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
a Erongation	7.91119	Agilig
Tensile Strength (Mpa)	30	28
ASTM Requirement Min. (Mpa)	18	14
Elongation (%)	900	860
ASTM Requirement Min. (%)	650	500



